

**CLEAN VERSION OF AMENDMENT**

**IN THE SPECIFICATION**

Please enter the following Substitute Specification and Abstract in replacement of the originally  
filed specification and Abstract.

**SUBSTITUTE SPECIFICATION**

**TITLE**

**A TRANSPARENT, ELASTIC AND FREE-STANDING COMPOSITION,  
SUCH AS FOR THE MANUFACTURE OF CANDLES, AND THE FREE-  
STANDING CANDLE OBTAINED WITH THE COMPOSITION**

**CLAIM OF PRIORITY**

**[0001]** This application makes reference to, incorporates the same herein, and claims all benefits  
accruing under 35 U.S.C. § 119 from an application entitled *A TRANSPARENT, ELASTIC AND*  
*SELF-SUPPORTING COMPOUND FOR THE MANUFACTURE OF CANDLES AND THE*  
*CANDLE OBTAINED WITH SAID COMPOUND* earlier filed in the Argentina National Institute of  
Industrial Property on September 15, 2000, and there duly assigned Application Number P  
000104870 by that Office and another application entitled *A TRANSPARENT, ELASTIC AND FREE-*  
*STANDING COMPOUND, FOR THE MANUFACTURE OF CANDLES, AND THE FREE-*  
*STANDING CANDLE OBTAINED WITH THE COMPOUND* earlier filed in the Argentina National  
Institute of Industrial Property on June 21 2001, and there duly assigned Application Number P  
010102961 by that Office.



## BACKGROUND OF THE INVENTION

### Field of the Invention

[0002] A main object of this invention is to provide a transparent, elastic and free-standing composition, such as for the manufacture of candles, and the candle obtained with this composition. The component of the present invention is suitable as a raw material in the manufacture of candles in general, thereby providing new possibilities for the structure of candles, which are difficult to achieve or obtain with the materials that are currently used in the main structure of candles, although possible uses for the composition of the present invention should not be construed in a limiting sense. "Transparent" is understood to mean the condition of allowing the passing of the light through the composition, such as through the body of a candle. "Elastic" is understood to mean the characteristic of allowing contraction and elongation deformations of the composition, when pressing the surface of the composition and then the composition, such as a candle made with the composition, returning to an original shape when the pressure is released.

[0003] Further, "free standing" is understood to mean the composition, such as a candle made with the composition, having the ability to stand by itself at room temperature, such that even during use of a candle made with the composition, such that the heat of the candlewick's combustion does not melt nor deform the body of the candle made with the composition of the present invention.

### Description of the Related Art

[0004] Traditional candles are known, such as those to be ignited and give light, which are formed having longer bodies, generally cylindrical, and with a lengthened candlewick included therein in

1 relation to the candle's longitudinal axis. Such traditional candles are manufactured with materials  
2 such as paraffin, wax, tallow or stearin. However, such conventional candles have the inconvenience  
3 that, though being self supporting, they are not transparent nor elastic, so their decorative and  
4 ornamental abilities are limited.

5 [0005] Also, there is a well-known "oil candle" that is liquid, and therefore, requires a container  
6 for its manufacture and for usage of the candle. However, such "oil candle" is typically  
7 disadvantageous as to decorative abilities and with respect to the outside structure of the candle  
8 since, invariably, such "oil candles" depend on a recipient that contains the fuel. Further,  
9 compositions for such "oil candles" have to be commercialized separately, since such candle has to  
10 be conformed by the user.

11 [0006] Different realizations disclosing composition compositions that can be applied to the  
12 formation of candles are known and include a mixture of hydrocarbon oil in a range between 90%  
13 and 70% proportion and one or more copolymers selected from a group of triblock and diblock  
14 polymers in a range between 2% and 30% proportion. This is due to the fact that, with such  
15 proportions, it is possible to form solid and transparent gels that can be molded by thermal treatment.  
16 However, it is not disclosed that such above-described transparent gels can conform to the body of  
17 a free-standing candle which does not deform nor flash when burned during its use.

18 [0007] In this regard, U.S. Patent No. 5,879,694 to Morrison *et al.* teaches a solid transparent  
19 gel candle including a hydrocarbon oil, a wick, and one or more triblock or multiblock copolymers,  
20 which constitute a thermoplastic elastic, and optionally uses a diblock copolymer. The preferred  
21 composition disclosed by Morrison *et al.* '694 contains from about 4% to about 20% polymer and

1 about 80% to about 96% of hydrocarbon oil, preferably white oil. The selected polymer is a triblock  
2 polymer as "Kraton® G type", more particularly "Kraton® G-1650". In this regard, Morrison *et al.*  
3 '694 discloses that preferably, clear glass jars are used for a jar candle.

4 [0008] Also, US Patent No. 6,066,329 to Morrison *et al.* discloses a transparent stiff gel candle  
5 including a hydrocarbon oil, a wick and one or more triblock or multiblock copolymers of a  
6 thermoplastic rubber, and optionally, a diblock copolymer. A preferred composition disclosed in  
7 Morrison *et al.* '329 contains from about 4 to about 20 percent of the polymer and from about 80  
8 to about 96 percent of a suitable hydrocarbon oil, preferable white oil. A preferred polymer is  
9 disclosed as a triblock polymer of the "Kraton® G type" particularly "Kraton® G 1650". Morrison  
10 *et al.* '329 also discloses as preferable to hold the candles in conventional jars, clear, colored,  
11 sculpted, cut glass jars, and preferably, clear glass jars are used for a jar candle.

12 [0009] US Patent No. 6,096,102 to Matthäi *et al.* disclose in particular, a candle built of a base  
13 material including between 93 and 98 weight percent of hydrocarbon oil "white oil" and between  
14 7 and 10 weight percent of a copolymer selected from the group of tri-block, radial block and  
15 multiblock copolymers and between 0 and 10 weight percent of a di-block copolymer. Matthäi *et*  
16 *al.* '102 combines a first component, which is formed by an oil, a copolymer and synthetic paraffin,  
17 with a second component including conventional paraffin, where the first component and the second  
18 component are arranged, alternately, in layers. In addition, Matthäi *et al.* '102 disclose that a  
19 transparent glass body is provided which surrounds a region of a candle base material and gives the  
20 candle structure.

21 [0010] US Patent No. 5,578,089 to Elsamaloty discloses a clear candle made with a gel including

1 a mineral oil combined with diblock and triblock copolymers based on synthetic thermal plastic  
2 rubbers. The clear candle is disclosed as stable, does not separate and does not flash when burned.  
3 The candle, it is disclosed, although free standing at room temperature, will preferably be supplied  
4 in a container, and it may be colored and/or scented. However, Elsamaloty '089 discloses that the  
5 container for a candle can include any of a variety of devices which can contain the gel, do not burn  
6 and do not melt, and, preferably, a faceted glass container can be used for aesthetic purposes. While  
7 Elsamaloty '089 discloses a clear candle could be provided without a container, due to the gel-like  
8 nature of the candle itself, and its potential flowability when heated, Elsamaloty '089 discloses that  
9 it is preferred that such candles include an appropriate container.

10 **[0011]** Further, U.S. Patent No. 6,111,055 to Berger *et al.* disclose the use of between 70 and  
11 98 weight percent of hydrocarbon oil with between 2 and 30 weight percent of a copolymer selected  
12 from a group of triblock, radial block and multiblock copolymers, and from 0 to 10 weight percent  
13 of a diblock copolymer. Berger *et al.* '055 also discloses the combination of a candle with the use  
14 of a solid coating placed around the candle to enhance mechanical stability of the gelled body.

## 15 SUMMARY OF THE INVENTION

16 **[0012]** It is an object, among other objects, of the present invention, to provide a transparent,  
17 elastic and free standing composition for the manufacture of free standing candles, formed with a  
18 mixture of a hydrocarbon oil in a relation of about 75 to about 88 in weight percent, typically 73 to  
19 88 weight percent and desirably 83.8 weight percent, and at least one copolymer selected from the  
20 group of triblock polymers and diblock polymers in a proportion from about 12 to about 25 in weight

1 percent, typically 12 to 27 weight percent and desirably 16.2 weight percent where the hydrocarbon  
2 oil has a viscosity of at least 180 SUS at 37°C (100°F) and, when the viscosity is in cSt, the viscosity  
3 of the hydrocarbon oil being greater than 32 cSt at 40°C (104°F), and the hydrocarbon oil having  
4 flash point greater than 220°C (425°F).

5 [0013] In a preferred embodiment of the composition of the present invention, the hydrocarbon  
6 oil has a viscosity of 340 SUS at 37°C (100°F) and when the viscosity is in cSt, the hydrocarbon oil  
7 has a viscosity greater than or equal to 67.8 cSt at 40°C (104°F), the hydrocarbon oil has a flash point  
8 at 240°C (464°F), and the selected copolymers are three-block polymers "Kraton ® G 1652".

9 [0014] Likewise, it is also the object, among other objects, of the present invention, to provide a  
10 free standing candle, manufactured with the mixture of: a hydrocarbon oil in a relation of about 75  
11 to about 88 in weight percent, typically 73 to 88 weight percent and desirably 83.8 weight percent,  
12 and at least one copolymer selected from the group of triblock and diblock polymers in a proportion  
13 of about 12 to about 25 in weight percent, typically 12 to 27 weight percent and desirably 16.2  
14 weight percent; where the hydrocarbon oil has a viscosity of at least 180 SUS at 37°C (100°F) and  
15 when the viscosity is in cSt, the viscosity of the hydrocarbon oil is greater than 32 at 40°C (104°F),  
16 and the flash point of the hydrocarbon oil being greater than 220°C (425°F), the candle maintaining  
17 a free standing condition when is lit by means of a flame produced as consequence of the combustion  
18 of a wick, the wick crossing the body of the candle and projecting toward outside one of its ends.  
19 Preferably, the candlewick is a cotton string, imbibed in an alcoholic solution of vegetal resin, such  
20 as pine resin. In the present invention due to the elasticity of the candle's composition, the  
21 candlewick is firmly retained in a passing hole produced when the composition of the present

1 invention is cold, the candlewick crossing the body of the candle in longitudinal correspondence to  
2 an axis of symmetry extending from an inferior or lower base of the candle.

3 **[0015]** Due to the above described special characteristics of the composition of the present  
4 invention, a free standing candle can be built by the union of a plurality of different format minor  
5 portions, wherein the minor portions are and individually made with a mixture of a hydrocarbon oil  
6 in a relation of about 75 to about 88 in weight percent, typically 73 to 88 weight percent desirably  
7 83.8 weight percent, and at least one copolymer selected from the group of triblock polymers and  
8 diblock polymers in a proportion from about 12 to about 25 in weight percent, typically 12 to 27  
9 weight percent and desirably 16. 2 weight percent, where the hydrocarbon oil has a viscosity of at  
10 least 180 SUS at 37°C (100°F) and, when viscosity is in cSt, the viscosity of the hydrocarbon being  
11 greater than 32 cSt at 40°C (104°F), and the flash point of the hydrocarbon oil being greater than  
12 220°C (425°F).

13 **[0016]** Also, the above-described mixture or composition of the present invention can include dye  
14 essences, which can be combined with aromatic fragrances, as well as air bubbles distributed in the  
15 part or all of the thickness of the candle and the air bubbles can be of different sizes. Likewise, the  
16 candle body of the present invention can include decorative elements arranged in the inner part of  
17 the thickness of the candle, which, due to the particular transparency of the composition of the  
18 present invention, the decorative elements can be visible from outside of the candle, which  
19 decorative elements are located in the portion of the composition forming the candle not adjacent  
20 to the candlewick.

**BRIEF DESCRIPTION OF THE DRAWINGS**

[0017] A more complete appreciation of this invention, and many of the attendant advantages thereof, will be readily apparent as the same becomes better understood by reference to the following detailed description when considered in conjunction with the accompanying drawings in which like reference symbols indicate the same or similar components, wherein:

[0018] Figure 1 is a perspective view illustrating an embodiment of a mold to conform a free standing candle made with the composition of the present invention;

[0019] Figure 2 is a perspective view illustrating a free standing candle of the present invention molded in the mold for Figure 1;

[0020] Figure 3 is a perspective view illustrating an embodiment of a free standing candle of the present invention formed by a plurality of minor portions made with the composition of the present invention and united one with each other to form a unitary candle body;

[0021] Figure 4 is a schematic perspective view illustrating a free standing inflamed candle of the present invention with the candlewick of the candle consumed to approximately half its height;

[0022] Figure 5 is a schematic perspective view illustrating an embodiment of a free standing inflamed candle of the present invention formed with the composition of the present invention, which includes a plurality of lit candlewicks;

[0023] Figure 6 is a schematic perspective view illustrating an embodiment of a free standing candle of the present invention formed with the composition of the invention, which includes granule particles, such as "purpurin" as a decorative element;

[0024] Figure 7 is a schematic perspective view illustrating an embodiment of a free standing



1 candle of the present invention formed with the composition of the invention, which includes air  
2 bubbles; and

3 **[0025]** Figure 8 is a schematic perspective view illustrating an embodiment of a free standing  
4 candle of the present invention formed with the composition of the invention, which includes  
5 decorative elements.

### 6 **DESCRIPTION OF THE INVENTION**

7 **[0026]** More specifically, the present invention relates to a composition obtained from the mixture  
8 of hydrocarbon oil, specially white oils, and block copolymers. The present invention relates to a  
9 composition, such as for use in a candle, that has a consistency to be free-standing, and maintaining  
10 elasticity features, while the composition maintains transparency, as well as the composition  
11 enabling the configuring of bodies of various shapes and designs. The composition of the present  
12 invention, has the special particularity of allowing the incorporation of at least one candlewick in  
13 to the candle, similar to those used by candles in general, to provide a combustion of a candle made  
14 with the composition of the present invention that generates a stable and lasting flame without giving  
15 off unpleasant odors.

16 **[0027]** The composition of the invention has been particularly created for the manufacture of  
17 transparent candles which, at the same time are free-standing, that is to say, which do not need a  
18 container that supports a candle made from the composition of the present invention. Candles made  
19 from the composition of the present invention also are elastic and unbreakable when they fall or  
20 receive sudden knocks, and such candles made from the composition of the present invention

1 desirably can be mixed with dyes and aromatic fragrances, as well as can include decorative elements  
2 within the candle that are noticeable from outside, or that provide other or inner functional resources  
3 related to the art of lighting and decorating different environments.

4 **[0028]** The above described composition of the present invention, in summary, advantageously  
5 has special qualities: it is transparent, free standing and elastic, with enough consistency to form a  
6 candle with a stable flame, that does not deform upon application of pressure and that does not get  
7 fluid during its use, such as when the candlewick is burning.

8 **[0029]** Using the composition of the present invention, it is possible to manufacture candles to  
9 have the following desirable features:

10 a) elasticity, so as to present a consistency solid enough to be self-supporting, without  
11 requiring a container for supporting the candle for its normal functioning;

12 b) resistance or resiliency to mechanical knocking or jarring without generating  
13 undesirable breaks, splits or contusions in the candle, as can happen with paraffin candles;

14 c) transparency, so that light can pass through the body of the candle;

15 d) the ability to be mixed with fragrances, so that the consumption of the candle during  
16 the flame action of burning of the candlewick or wicks also produces the release of pleasant odors;

17 e) the ability to be mixed with dyes, which is desirable from an aesthetic or ornamental  
18 point of view

19 f) during manufacturing, generating the presence of air bubbles of various sizes such  
20 that distribution of air bubbles in the body of the candle can be achieved, which is useful as  
21 decorative resources;

1           g)       mixing the composition of the present invention with other decorative elements such  
2 as various types and sizes of granule particles so as to be distributed in the thickness of the candle  
3 body, so as to be visible from outside of the candle, and decorative elements can be even more  
4 enhanced when the candle is lit, such as granule products that reflect light in various colors, such as  
5 those commonly called “purpurin” and/or “brilliantine”;

6           h)       supporting within the body of the candle of an appropriate thickness, other products  
7 or decorative bodies such as letters, numbers, little animals or other objects; and

8           i)       the composition of the present invention being a reversible or recyclable composition,  
9 since upon heating, melting, and then cooling the composition to room temperature, the candle  
10 formed of the composition of the present invention keeps the same constituent features.

11 **[0030]** Likewise, it is highlighted that all of the above described features and conditions in relation  
12 to the composition of the present invention can be maintained without affecting each other.

13 **[0031]** The reasons for the composition of the present invention providing superior and  
14 unexpected type results, are related to the chemical characteristics of the hydrocarbon oil, such as  
15 a white oil. When the values for the hydrocarbon oil and copolymer specified for the composition  
16 of the composition of the present invention are maintained, a very special relation between the  
17 viscosity and the flash point is achieved. In this regard, when the values of the hydrocarbon oil and  
18 copolymer are below the specified values for the composition of the present invention, the  
19 composition could be free standing at room temperature but the heat of the wick's combustion can  
20 melt the composition to a liquid point. On the other hand, when more polymer than what is specified  
21 in the present invention is used to harden the composition or composition, the composition or

composition can inflame with the combustion produced by the candle's wick.

[0032] The above-described composition of the present invention is prepared mixing the hydrocarbon oil with a triblock copolymer, heating this mixture and stirring it regularly until it reaches 150-160° C, which is equivalent to 302-320° F. Stirring the mixture, mechanically or manually, is convenient to achieve the desirable dissolution of the polymer in the hydrocarbon oil. The hydrocarbon oil used for the composition of the present invention is desirably white oil ("Vaseline") having the following characteristics as set forth in <TABLE 1>.

<TABLE 1>

Specification	Value	Method
VISCOSITY SUS@ 37.8°C (100°F)	345	ASTMD 88
VISCOSITYcSt@ 40°C (104°F)	32 (67.8)	ASTM D 445
DENSITY @ 20°C (68°F)	0.88	ASTM D 1298
FLASH POINT	240° C (464°F)	ASTM D 97
TURBIDITY POINT	-5° C (23° F)	ASTM D 2500
COLOR AL PT-CO (EX ALPHA)	10	ASTM D 1209
ASTM= American Society for Testing and Material (site:www.astm.org)		
METHOD= Method of analysis		
SUS and cSt (centistokes) are measure units of each essay		

[0033] Two of these values for the hydrocarbon oil of TABLE 1 are very important when choosing the hydrocarbon oil, such as the white oil ("Vaseline"), which are: the flash point desirably should not be inferior to or less than 200°C (392 °F) and the viscosity desirably should not be inferior to or less than 32 cSt, desirably at least 67.8 cSt.

[0034] The other values for the hydrocarbon oil in TABLE 1 can change, dependent upon the

specifications of the product, without altering the preparation of the composition of the present invention.

[0035] In relation to the triblock copolymer used in the above-described composition or composition of the present invention, the most desirable is a triblock copolymer with polystyrene end blocks and a rubbery poly (ethylene butylene) mid block. The polymer used in the preparation of composition of the present invention desirably should have the following preferred characteristics as set forth in <TABLE 2>.

<TABLE 2>

Tensile strength, psi	4,500
Elongation at break, %	500
Modulus at 300% extension, psi	700
Film appearance	Clear, water white
Solution viscosity *25% w in toluene,cps	1800
Melt viscosity, melt index, condition G, Gms-10 min	1
Styrene-rubber ratio	30-70
* Brookfield viscosity meter Model RTV to 25°C (77°F)	

[0036] Polymers that better suit the above-described characteristics set forth in <TABLE 2> are Kraton® G 1652 of Shell Chemicals, for example.

[0037] To prepare the above-described composition of the present invention, hydrocarbon oils are used that have the feature of remaining liquid within a temperature range between 0°C(32°F) and 200 °C (392°F), as well as the condition of being transparent and of high density. One of the hydrocarbon

oils that best adapts to these conditions is a 180 density white oil ("Vaseline"). Likewise, for the composition of the composition of the present invention the above-described polymers are used.

**[0038]** The first step in preparing the composition or mixture of the present invention is to mix two-block or three-block polymers, especially an S-EB-S chain, which are capable of retaining more than twenty times its weight in hydrocarbon oil. Among known polymers suitable for use in the present invention, there are different kinds of polymers, but those of "Kraton® Series G" are the best or preferred for use in the composition or mixture of the present invention. These "Kraton® G" series polymers correspond to a type of three-block polymer, such as "S-EB-S" type. It is also possible to use "Kraton® Series D" type, but they typically do not achieve as good a result as in the previous case. The quantity of polymer to be used in the composition or mixture of the present invention relates to the level of hardness intended for the mixture.

**[0039]** Starting from the previously mentioned elements of the hydrocarbon oil and copolymer, the process then proceeds to mix the mixture of the hydrocarbon oil and copolymer through normal stirring, at a temperature ranging from 80 °C (176°F) to 160 °C (320°F), up to the solubilization of the mixture and that leaves the solution transparent.

**[0040]** Referring to Fig. 1, for the pouring in molds, materials of container P and mold M of delicate finish and that resist temperatures up to 160 °C may be used. Varying the temperature and speed of pouring of the mixture or composition C of the present invention these can be obtained variations in relation to the final finish of the composition C of the present invention, which can include air bubbles of different sizes or can be without air bubbles. In Fig. 1 a mold M for the function of forming a candle of the present invention is illustrated, the mold M having a completely

open superior or upper base, and the mold M having an internal diameter a and a height b, as illustrated in Fig. 1. For the pouring of the composition C from the container P to inside the mold M, the mold M must be able to resist without deforming temperatures of up to 160° C (320 ° F), and in this regard, stainless steel, brass, aluminum, copper, bronze, silicon rubber *etc.* are the most convenient and desirable materials used for the mold M. In relation to the interior surface 1 of the mold M, it is very important that the interior surface 1 be brilliant, neat and polished, so that the composition C when formed into a candle of the present invention will have the same neatness and brightness. By changing the temperature and the speed of the pouring of the composition C from the container P to inside the mold M, various different finishes can be obtained for the candle of the present invention.

**[0041]** Once the composition C cools in the mold M to room temperature, a completely clear, transparent composition without air bubbles is obtained when pouring the composition C in the mold M at a temperature between 150°C(302°F) and 160°C (320°F) to provide a clear, transparent candle as candles 100, 100A, 100B and 100C of Figs. 2 through 5.

**[0042]** When the temperature of the composition C is between 100°C(212°F) and 120°C(248°F) when pouring the composition C into the mold M, the composition C will have air bubbles 2 when it cools to room temperature to provide a clear, transparent candle having air bubbles 2, such as candle 100E of Fig. 7. Air bubbles 2 can also appear in the composition C when the speed and the height of the pouring are changed, since that allows the entrance of more air or less air into the composition C.

1     **[0043]** Figure 2 represents a free standing candle 100 already formed according to the format and  
2     dimensions of the mold M of Fig. 1. For the shaping of a candle of the present invention, the  
3     composition C is capable of keeping the candlewick 3 in a similar way as it is disposed in  
4     conventional candles. Conventional paraffin candlewick, as well as candlewicks for gel or especially  
5     prepared for these types of candles, such as a cotton string imbibed in a solution of vegetal resin,  
6     such as pine resin, can be used for candlewick 3. The candlewick 3 can be placed during the  
7     manufacture of the candle, such as candle 100, in the traditional way, that is to say, arranging same  
8     in correspondence with the longitudinal axis X of the mold M and the candle extending from a lower  
9     base 1a of the candle (Figs. 1 and 2) and fixing the candlewick 3 so as to be stretched or erected so  
10    as not to move while the mixture or composition C is poured into the mold M.

11   **[0044]** It is also possible to place candlewick 3 in the candle by taking advantage of the feature  
12   of elasticity of the composition C of the present invention. Therefore, once the candle has been  
13   shaped in the mold M, there is made an aperture or a passing hole 4 in the candle, such as candles  
14   100B and 100D of Figs. 4 and 6 through which the entire candlewick 3 moves forward till the  
15   candlewick 3 is arranged in a condition of usage in the candle. The passing hole 4 is produced when  
16   the candle desirably is at room temperature, the passing hole 4 extending through the candle in  
17   longitudinal correspondence to an axis of symmetry L extending from a lower base B of the candle,  
18   such as in candles 100B and 100D of Figs. 4 and 6. The candlewick 3 is kept stable in the candle,  
19   such as in candles 100B and 100D, without relative displacement due to the mentioned elasticity of  
20   the material or composition C of the present invention.



1     **[0045]**     Considering the foregoing, it is possible to shape candles, such as candles 100 through  
2     100F of Figs. 2 through 8, of different sizes and dimensions, which will have a minimum size that  
3     depends on the candlewick 3 size used, since the combustion temperature generated and the quantity  
4     of adjacent material melted of the candle depends on the type and proportions of the candlewick 3  
5     used in the candle. It is possible to manufacture candles of different forms and sizes taking into  
6     account the candlewick 3's thickness and the melting diameter of the candle in relation to candle's  
7     minimum diameter.

8     **[0046]**     In the candles of the present invention, such as candles 100 through 100F, providing a  
9     candle diameter larger than the melting diameter of the candle, a decorative effect can be achieved  
10    that is highly pleasant, since the portion of the material or composition C in the candle that is not  
11    melted keeps its original structure. For example, a candle of a diameter which is twice the melting  
12    diameter of the candle produced during the combustion of a candlewick 3; 3a, 3b, 3c, produces a  
13    tunneling 5, 5a, 5b, 5c since the candlewick's flame 6, 6a, 6b, 6c will melt a certain diameter of the  
14    composition C around the candlewick 3, 3a, 3b, 3c but the rest of the candle will remain unchanged.  
15    The flame 6, 6a, 6b, 6c consumes the candlewick 3, 3a, 3b, 3c during the combustion and, as  
16    consequence, the candlewick 3, 3a, 3b, 3c- is shortened by such combustion, and the light produced  
17    by the flame 6, 6a, 6b, 6c inside the candle, such as candles 100B through 100F of Figs. 4 through  
18    8, for example, will go through the transparent body of the candle achieving a very special, beautiful  
19    and unique effect.

20    **[0047]**     Fig. 3 illustrates a free standing candle 100A of the present invention built with a plurality  
21    of minor portions 7, 8 and 9 of the composition C, the minor portions being of different sizes and

1 forms. The minor portions 7, 8 and 9 forming the candle 100A can be formed by different methods,  
2 such as molding, lamination, extrusion, *etc.* When the minor portions 7, 8 and 9 are united one with  
3 the other to form a unitary structure, a free standing candle 100A as illustrated in Fig. 3, having  
4 properties of candles of the present invention, as previously mentioned is provided.

5 **[0048]** The composition C's shapes and formats obtained for the above-mentioned minor portions,  
6 such as minor portions 7, 8 and 9, can be laminar, cylindrical, rectangular, and any other suitable  
7 design. By using heat to melt the composition C of the present invention in the desired joint point  
8 J of two of the minor portions obtained, the melted composition of both minor portions will mix and,  
9 once cooled, the minor two portions are united forming one single piece of a unitary structure. This  
10 allows an artist, for example, to design and manufacture candles of varying shapes and designs by  
11 making and joining minor portions formed of the composition C of the present invention having  
12 different colors, finishes and shapes.

13 **[0049]** Referring to Fig. 5, an embodiment of a candle 100C of the present invention is illustrated  
14 formed of the composition C of the present invention that allows the formation of free standing  
15 candles of a relatively large diameter so as to allow the placing of more than one candlewick 3 in the  
16 candle. In the candle 100C of Fig. 5, a plurality of candlewicks 3a, 3b, 3c are illustrated which are  
17 reduced by their combustion generating tunnelings 5a, 5b, 5c lightened with flames 6a, 6b, 6c.

18 **[0050]** Further, the composition C of the present invention also allows the possibility of  
19 composition C of candles 100 through 100F of Figs. 2 through 8 being mixed with colorants by  
20 adding dyes to color the composition C and, also, the composition C of candles 100 through 100F

1 of Figs. 2 through 8 can be mixed with aromatic fragrances to perfume the ambient air during the  
2 combustion of the candlewicks 3a, 3b, 3c.

3 [0051] Additionally, Fig. 6 illustrates a candle 100D of the present invention where the  
4 composition C of the present invention has been mixed with a granular material 10, such as  
5 “purpurin”, for example.

6 [0052] Also, Fig. 8 illustrates a candle 100F of the present invention where the body of the candle  
7 100F has a plurality of different decorative elements 11a through 11d, for example, distributed in  
8 the interior of the candle 100F. The placing of the decorative elements 11a through 11d, for  
9 example, in the body of the candle 100F can be allowed by placing the decorative elements 11a  
10 through 11d, for example, in the composition C of the present invention once is poured from  
11 container P into the mold M (Fig. 1) and before the composition cools to room or ambient  
12 temperature. Such decorative elements can also include a logo, a name, a picture, an object, *etc.*, for  
13 example, set in the composition C of the candle before cooling of the composition to room or  
14 ambient temperature. The composition C of the present invention will hold the decorative elements  
15 11a through 11d, for example, and, due to the composition C's transparency, the decorative elements  
16 11a through 11d, for example, will be visible from outside of the candle, such as illustrated in candle  
17 100F of Fig. 8.

18 [0053] The following Examples 1 and 2 are now described to illustrate exemplary embodiments  
19 of the composition or mixtures and candles of the present invention.

**Example 1:**

[0054] A mixture of the present invention containing white oil in a relation of 75 to 88 weight percent and a three-block polymer of "Kraton® G series" type in a relation of 25 to 12 weight percent was prepared. This composition was obtained heating the mixture at a temperature ranging between 100° C (212° F) and 160° C (320° F), desirably 150° C (302° F) to 160° C (320° F), stirring till the mixture becomes clear and transparent. In this case, a dye and an aromatic fragrance were added and the obtained mixture was poured in a cylindrical mold of 7 cm diameter and 7 cm of height proceeding to its cooling and hardening.

[0055] Once the mixture of composition is cooled, at room temperature, the demolding was accomplished and the placement of the candlewick or wick was performed. In this case the candlewick was formed by a cotton string imbibed in an alcoholic solution of pine resin. A passing aperture or passing hole in correspondence to the axis of symmetry of the cylindrical body of the candle was formed, in which the candlewick was introduced. From the above-described process, a free standing, transparent and color candle was obtained. The candle thus formed kept a flame, as a product of the combustion generated from the candlewick, which flame maintained constant during 40 continuous hours of burning.

**Example 2:**

[0056] A mixture of the present invention of hydrocarbon oil and copolymer similar to that of Example 1 was prepared, and, previous to the stage of cooling, the mixture or composition thus

1 prepared was poured in a plurality of different molds to provide a plurality of minor portions. These  
2 minor portions poured into the plurality of different molds were mixed with different coloring  
3 essences and then exposed to cooling individually, as explained previously. In this regard, different  
4 forms and shapes of compositions were obtained, such as sheets of different sizes, strings of different  
5 thickness, as well as portions without defined format, all of them in varying colors, as explained  
6 previously.

7 **[0057]** Using the above-mentioned minor portions in a solid state, a handmade design of different  
8 structures were performed assigned to shape candles; and the plurality of different minor portions  
9 were joined together, applying heat, thus obtaining candle bodies of different shapes and sizes, as  
10 explained previously, having a unitary structure for the candle body formed from the different minor  
11 portions. A corresponding candlewick was introduced in the body of the thus formed candle,  
12 following the same method explained in the previous Example 1.

13 **[0058]** While there have been illustrated and described what are considered to be preferred  
14 embodiments of the present invention, it will be understood by those skilled in the art that various  
15 changes and modifications may be made, and equivalents may be substituted for elements thereof  
16 without departing from the true scope of the present invention. In addition, many modifications may  
17 be made to adapt a particular situation to the teaching of the present invention without departing  
18 from the scope thereof. Therefore, it is intended that the present invention not be limited to the  
19 particular embodiments disclosed as the best mode contemplated for carrying out the present  
20 invention, but that the present invention includes all embodiments falling within the scope of the  
21 appended claims.